




Exlfilm fresh®AF performance shrink film uses cross-linked technology that provides consistent sealing and shrinking at a wide range of temperature. Exlfilm fresh®AF is engineered with unique anti-fog properties to maintain clarity for product presentation in refrigerator applications.

- Anti-Fog properties ensure clarity and enhance retail product presentation attracting more customers. Ideal for shrink packaging of fresh fruits, vegetables, meat and fresh products.
- Maximum available shrinkage ensures that the film conforms to the most irregularly shaped products, providing superior product presentation.
- Exceptional tensile strength and tear resistance gives added durability and toughness to ensure your product is better protected.
- Complies with standards for direct food contact.

CROSSLINKING TECHNOLOGY





Anti-Fog Shrink Film

TECHNICAL DATA SHEET

Thickness [μm]	Length [m]					
	Flat				Centerfolded	
09	27.600	13.800	9.200	4.600	4.600	2.300
11	22.500	11.250	7.500	3.750	3.750	1.875
12,5	19.800	9.900	6.600	3.300	3.300	1.650
15	16.500	8.250	5.500	2.750	2.750	1.375

Properties		Test Method	Thickness [μm]			
			09	11	12,5	15
Yield (m2/kg)		-	120,8	98,8	86,9	72,5
Unit Weight (g/m2)		-	8,3	10,1	11,5	13,8
Heat Shrinkage (%)	MD	120°C, air and 5 min MIE 002	74			
	TD		72			
Tensile Strength (MPa)	MD	ASTM D882	133			
	TD		138			
Elongation at Break (%)	MD		120			
	TD		110			
Gloss at 20° (%)		ASTM D 2457	109			
Haze (%)		ASTM D 1003	4,2			
Coefficient of friction		ASTM D 1894	0,28			
OTR ⁽¹⁾ (cm3/(m2.24h.atm)		ASTM D 3985/ASTM F 1927	10.400			
WVTR (2) (g /h.m2)		ASTM E 96/E96M	1,4			

Note: These values are typical and not intended as limiting specifications.

⁽¹⁾ 15μm, 23°C & dry gas inside/dry gas outside. ⁽²⁾ 15μm, 50%RH, 38°C

Cardboard core internal 76,6mm. Flat width from 200mm up to 1200mm with increments of 10mm. Centerfolded width from 150mm up to 1000mm with increments of 50mm. Other specifications available upon request.

Storage time should not exceed 12 months. The maximum storage temperature for optimum performance is 35°C.

Effective:07/23



Fibope complies with the requirements and regulations which state that materials may be used in food contact applications. For more information contact our technical support team. While we believe them to be reliable the statements and information herein are only for general guidance and are not warrants or guarantees for accuracy and completeness. The use must, by test or otherwise, determine suitability for this purpose. Our standard term and conditions of sale apply exclusively to all orders, and all liability for damages of any kind, including consequential exceeding purchase price is excluded. No one is authorized by us to make oral warranties. We reserve the right to make changes without notice or obligation in our products and publications.



FIBOPE PORTUGUESA – FILMES BIORIENTADOS, SA is an industrial company dedicated to the production of flexible films for packaging, integrated in the group “Intertape Polymer, Inc.”, of Canada. We produce films based on polyolefins, bi-oriented and co-extruded (polyolefin shrink film) in multi-layers. Being a modern unit based on a favorable costs structure and advanced production techniques, it is able to meet the needs of its customers.

FIBOPE practices a continuous policy of quality and development of its capacities to satisfy the requirements of the customers regarding the products and services it offers, being certified since 2001, according to NP EN ISO 9001: 2008 and from 2013 according to the BRC / IOP reference Packaging.

The quality of the products Exfilm®, Exfilmplus®, Exfilmfresh® and Exfilmeco® is constantly tested in our laboratory, equipped with highly sophisticated equipment and qualified technicians, allowing to guarantee quality and consistency.

The main applications are directed to the packaging of food products, cosmetics, paper and display market in general. The concept of total compliance with our customers guides daily activities and differentiates FIBOPE from competitors.

Estrada da Praia, nº 1087
4740 – 696 Barqueiros BCL Portugal
Tel.: +351 253 859 270
Email: fibope@fibope.pt