@Exlfilmplus®






Exlfilmplus®LSF is a perfect combination of high shrinkage and a low shrink force. Indicated for thin or delicate and sharp products. Exlfilmplus®LSF is soft cross-linked shrink for a wide range of packaging applications. Perfect for papers products, magazines, gift wrap, etc.

- Strong and durable seals.
- High gloss and clarity.
- Low shrink force to avoid the distortion of flexible products or buckling around the products.
- Complies with standards for direct food contact.

CROSSLINKING TECHNOLOGY

This innovative technique makes Exlfilmplus® Shrink Films one of the toughest and most versatile on the market. This is because the polymer chains are permanently bound into a network, significantly increasing their heat stability and strength. Our films have an inherently greater window of seal and shrink performance at a broader range of temperatures.

- Prevention of Buildup on wires and knives during sealing
- Prevention of Film Burn-Through in heat tunnels
- Increased Film Toughness on the finished package







TECHNICAL DATA SHEET

| Thickness | Length [m] | | | | | | | | | |
|-----------|------------|--------|-------|-------|--------------|-------|--|--|--|--|
| [µm] | | Flat | | | Centerfolded | | | | | |
| 11 | 22.500 | 11.250 | 7.500 | 3.750 | 3.750 | 1.875 | | | | |
| 12,5 | 19.800 | 9.900 | 6.600 | 3.300 | 3.300 | 1.650 | | | | |
| 15 | 16.500 | 8.250 | 5.500 | 2.750 | 2.750 | 1.375 | | | | |
| 19 | 12.900 | 6.450 | 4.300 | 2.150 | 2.150 | 1.075 | | | | |
| 25 | 9.000 | 4.500 | 3.000 | 1.500 | 1.500 | 750 | | | | |

| Properties | | Toot Mathead | Thickness [μm] | | | | | |
|-------------------------|----|----------------------|----------------|------|------|------|-------|--|
| | | Test Method | 11 | 12,5 | 15 | 19 | 25 | |
| Yield (m2/kg) | | - 98,8 | | 86,9 | 72,6 | 57,2 | 43,48 | |
| Unit Weight (g/m2) | | - | 10,1 11,5 13,8 | | 17,5 | 22,9 | | |
| Heat Christians (0/) | MD | 120°C, air and 5 min | 76 | | | | | |
| Heat Shrinkage (%) | TD | MIE 002 | 75 | | | | | |
| Tensile Strength | MD | | 110 | | | 106 | | |
| (MPa) | TD | ACTAA DOOG | 115 | | | 108 | | |
| Elongation at Break | MD | - ASTM D882 | 138 | | | 147 | | |
| (%) | TD | | 117 | | | 126 | | |
| Gloss at 20° (%) | | ASTM D 2457 | 122 | | | 108 | | |
| Haze (%) | | ASTM D 1003 | 3,4 | | | 4 | 4,4 | |
| Coefficient of friction | | ASTM D 1894 | 0,2 | | | | | |
| Shrink Force at | MD | MIE 010 | 0,32 | 0,39 | 0,41 | 0,56 | 0,60 | |
| 100°C (N) | TD | MIE 019 | 0,42 | 0,50 | 0,70 | 0,82 | 1,00 | |

Note: These values are typical and not intended as limiting specifications.

Cardboard core internal 76,6mm. Flat width from 200mm up to 1200mm with increments of 10mm. Centerfolded width from 150mm up to 1000mm with increments of 50mm. Other specifications available upon request.

Storage time should not exceed 12 months. The maximum storage temperature for optimum performance is 35°C.





is able to meet the needs of its customers.







Effective:12/23

Fibope complies with the requirements and regulations which state that materials may be used in food contact applications. For more information contact our technical support team. While we believe them to be reliable the statements and information herein are only for general guidance and are not warrants or guarantees for accuracy and completeness. The use must, by test or otherwise, determine suitability for this purpose. Our standard term and conditions of sale apply exclusively to all orders, and all liability for damages of any kind, including consequential exceeding purchase price is excluded. No one is authorized by us to make oral warranties. We reserve the right to make changes without notice or obligation in our products and publications.







FIBOPE practices a continuous policy of quality and development of its capacities to satisfy the requirements of the customers regarding the products and services it offers, being certified since 2001, according to NP EN ISO 9001: 2008 and from 2013 according to the BRC/ IOP reference Packaging.

FIBOPE PORTUGUESA - FILMES BIORIENTADOS, SA is an industrial company dedicated to the production of flexible films for packaging, integrated in the group "Intertape Polymer, Inc.", of Canada. We produce films based on polyolefins, bi-oriented and co-extruded (polyolefin shrink film) in multi-layers. Being a modern unit based on a favorable costs structure and advanced production techniques, it

The quality of the products Exlfilm®, Exlfilmplus®, Exlfilmfresh® and Exlfilmeco® is constantly tested in our laboratory, equipped with highly sophisticated equipment and qualified technicians, allowing to guarantee quality and consistency.

The main applications are directed to the packaging of food products, cosmetics, paper and display market in general. The concept of total compliance with our customers guides daily activities and differentiates FIBOPE from competitors.